

Amendments to the Claims

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

Claims 1-8 (canceled).

Claim 9 (currently amended): A resin coated steel sheet comprising a galvanized alloy steel sheet and an organic resin layer formed on at least one surface of said galvanized steel sheet;

wherein a galvanized alloy plating is formed on at least one surface of a steel sheet and the sheet having the galvanized alloy thereon is treated with an anodic treatment in acid solution, wherein the composition of the acid solution is the same as a bath composition of the galvanized alloy plating bath wherein hydrate oxides selected from the group consisting of Zn, Co, Ni and Mo are formed on the galvanized alloy, wherein the at least one surface of the galvanized alloy steel sheet is blackened to have an L-value equal to or less than 30.

Claim 10 (currently amended): A resin coated steel sheet comprising a galvanized alloy steel sheet and an organic resin layer formed on at least one surface of the galvanized alloy steel sheet, wherein a galvanized alloy plating is formed on at least one surface of a steel sheet and the sheet

having the galvanized alloy thereon is treated by an anodic treatment in acid solution, wherein the composition of the acid solution is the same as the composition of the galvanized alloy plating bath wherein hydrate oxides selected from the group consisting of Zn, Co, Ni and Mo are formed on the galvanized alloy, wherein the at least one surface of the galvanized alloy steel sheet is blackened to have an L-value equal to or less than 30, and said organic resin layer includes at least one of colloidal silica and an agent providing a lubricant function at a surface of the organic resin layer.

Claim 11 (previously presented): The resin coated steel sheet according to claim 9 wherein the resin is selected from the group consisting of urethane resins, polyester resins, acrylic resins, and olefin resins.

Claim 12 (previously presented): The resin coated steel sheet according to claim 10 wherein the resin is selected from the group consisting of urethane resins, polyester resins, acrylic resins, and olefin resins.

Claim 13 (previously presented): The resin coated steel sheet according to claim 9 wherein the resin is a urethane resin having a pencil hardness of individual resin of H to 6H, a tensile strength of 300 to 500 kg/cm² and an extension ratio of 250 to 450%.

Claim 14 (previously presented): The resin coated steel sheet according to claim 10 wherein the resin is a urethane resin having a pencil hardness of individual resin of H to 6H, a tensile strength of 300 to 500 kg/cm² and an extension ratio of 250 to 450%.

Claim 15 (previously presented): The resin coated steel sheet according to claim 10 wherein the organic resin layer includes colloidal silica of equal to or less than 50 wt%, polytetrafluoroethylene, and optionally 20 wt% or less of at least one of polytetrafluoroethylene or polyethylene wax.

Claim 16 (previously presented): The resin coated steel sheet according to claim 9 wherein the organic resin layer includes at least one member of the group consisting of 0.01 to 3 wt% anti-rust agent, 0.05 to 1 wt% silane coupling agent, and 0.1 to 3.0 wt% black pigment.

Claim 17 (previously presented): The resin coated steel sheet according to claim 10 wherein the organic resin layer includes at least one member of the group consisting of 0.01 to 3 wt% anti-rust agent, 0.05 to 1 wt% silane coupling agent, and 0.1 to 3.0 wt% black pigment.

Claim 18 (previously presented): A patrone cap made of a resin coated steel sheet according to claim 9.

Claim 19 (previously presented): A patrone cap made of a resin coated steel sheet according to claim 10.

Claim 20 (previously presented): A patrone body made of a resin coated steel sheet according to claim 9.

Claim 21 (previously presented): A patrone body made of a resin coated steel sheet according to claim 10.

Claim 22 - 23 (canceled).